



Tabella Kg/Mt

Tubi trafilati a freddo senza saldatura

Diam. Est. Spess.	4	5	6	7	8	9	10	11	12	13	14	15	16	17	18	19,05	20	21	22	23	24	25	25,4	
1	0,074	0,099	0,123	0,148	0,173	0,197	0,222		0,271	0,296	0,321	0,345	0,370		0,419		0,469		0,518				0,592	
1,5			0,166		0,240		0,314	0,351	0,388	0,425	0,462	0,499	0,550	0,573	0,610		0,684		0,758			0,832	0,869	
1,65																0,696								
2			0,197	0,247	0,296		0,395	0,444	0,493	0,543	0,592	0,641	0,691	0,740	0,789		0,888	0,937	0,986	1,036	1,085	1,134		
2,11																0,884								1,198
2,5					0,339		0,462		0,586	0,647	0,709	0,771	0,832	0,894	0,956		1,079	1,141	1,202	1,264	1,326	1,387		
2,77																								1,510
3							0,518		0,666	0,740	0,814	0,888	0,962	1,036	1,110		1,258	1,332	1,406	1,480	1,554	1,628		
3,5							0,562					0,993	1,079	1,165	1,252		1,424	1,511	1,597			1,856		
4									0,789		0,986	1,085	1,184	1,282	1,381		1,578	1,677	1,776			1,973	2,072	
4,5																	1,720		1,942				2,275	
5												1,233	1,356	1,480	1,603		1,850	1,973	2,096			2,343	2,466	
5,5																	1,967							
6															1,776				2,368			2,663	2,811	

Diam. Est. Spess.	26	27	28	30	32	34	35	36	38	40	42	45	48	50	51	52	55	56	57	58	60	64	65	
1				0,715																				
1,5		0,943	0,980	1,054	1,128		1,239		1,350	1,424	1,498	1,609		1,794								2,164		
2	1,184	1,233	1,282	1,381	1,480	1,578	1,628	1,677	1,776	1,874	1,973	2,121	2,269	2,368	2,417		2,614	2,663				2,861		
2,5	1,449	1,511	1,572	1,695	1,819		2,004		2,189	2,312	2,435	2,620		2,929	2,990		3,237					3,545		3,853
3	1,702	1,776	1,850	1,998	2,146	2,294	2,368	2,441	2,589	2,737	2,885	3,107	3,329	3,477	3,551	3,625	3,847		3,995	4,069	4,217	4,513	4,587	
3,5	1,942	2,028		2,287	2,460					3,151	3,323								4,618					
4	2,170	2,269	2,368	2,565	2,762	2,959	3,058	3,157	3,354	3,551	3,749	4,044	4,340	4,538		4,735	5,031				5,327	5,524		6,017
4,5				2,830																				
5	2,589	2,713	2,836	3,083	3,329	3,576	3,699	3,823	4,069	4,316	4,562	4,932	5,302	5,549		5,795	6,165		6,412			6,782		7,398
6		3,107	3,255	3,551	3,847	4,143	4,291	4,439	4,735	5,031	5,327	5,771	6,215	6,511		6,807	7,250		7,546			7,990		8,730
7				3,971	4,316	4,661			5,352	5,697	6,042													
7,5				4,162			5,086			6,011		6,936		7,861			8,786					9,710		10,64
8					4,735		5,327		5,919	6,313	6,708	7,300	7,892	8,286			9,273					10,26		11,25
9						5,549			6,437															
10							6,250			7,398	7,892	8,632		9,865			11,10					12,33		13,56



Tabella Kg/Mt

Tubi trafilati a freddo senza saldatura

Diam. Est. Spess.	70	75	76	80	82	85	90	95	100	105	110	115	120	125	130	135	140	145	150	155	160
2,5	4,162	3,601		4,778		5,086	5,395	5,703	6,011	6,320	6,628	6,936	7,244	7,553							
3	4,957	5,327	5,401	5,697	5,845	6,067	6,437		7,177												
4	6,511	7,004		7,497		7,990	8,484		9,470		10,46	10,95	11,44		12,43				14,40		15,39
5	8,015	8,632		9,248		9,865	10,48	11,10	11,71	12,33	12,95	13,56	14,18	14,80	15,41	16,03	16,65	17,26	17,88		19,11
6	9,470			10,95					13,91												
7,5	11,56	12,48		13,41		14,33	15,26	16,18	17,11	18,03	18,96	19,88	20,81	21,73				25,43			
8	12,23	13,22		14,21		15,19	16,18	17,16	18,15			21,11									
10	14,80	16,03		17,26		18,50	19,73	20,96	22,20	23,43	24,66	25,89	27,13	28,36	29,59		32,06	33,29	34,53		36,99



EN 10305-4 E235 + N (EX ST 37.4 DIN 2391 NBK -Normalizzato-)



EN 10305-1 E235 + A (EX Fe 35.2 UNI 663/68 GBK -Ricotto-)



EN 10305-1 E255 + N (EX Fe 45.2 UNI 663/68 NBK -Normalizzato-)